

TECHNICAL INFORMATION

1555 CENTRE POINT


TECHNICAL SPECIFICATIONS ACCORDING TO EN 1307

constructie	<i>construction</i>	ISO 2424	1/8" bouclé
poolmateriaal	<i>yarn content</i>	ISO 2424	100% wool
rug	<i>backing</i>	ISO 2424	Starback
gebruiksklasse	<i>suitability</i>	EN 1307	23 / 32 general contract use
poolgewicht	<i>pile weight</i>	ISO 2424	1050 gr/m ²
totaal gewicht	<i>total weight</i>	ISO 8543	2125 gr/m ²
pooldikte	<i>pile height</i>	ISO 1766	3.2 mm
totaal dikte	<i>total thickness</i>	ISO 1765	6.4 mm
noppental	<i>tuft density</i>	ISO 1763	104,000 tufts/m ²
breedte	<i>width</i>	CEN/TS 14159	ca. 4m / 5m
warmtedoorlaatweerstand	<i>thermal resistance</i>	ISO 8302	0.13 m ² K/W
brandklasse	<i>flammability</i>	ISO 13501-1	Bfl-s1
contactgeluidsisolatie	<i>impact sound insulation</i>	ISO 140-8/717-2	25 dB
structure	<i>Konstruktion</i>	ISO 2424	Fein Schlinge
composition	<i>Polmaterial</i>	ISO 2424	100% Schurwolle
dossier	<i>Beschichtung</i>	ISO 2424	Starback
classement d'usage	<i>Zusatzeignung</i>	EN 1307	23 / 32 general contract use
poids de velours	<i>Poleinsatzgewicht</i>	ISO 2424	1050 gr/m ²
poids total	<i>Gesamtgewicht</i>	ISO 8543	2125 gr/m ²
hauteur du velours	<i>Polschichtdicke</i>	ISO 1766	3.2 mm
épaisseur totale	<i>Gesamtdicke</i>	ISO 1765	6.4 mm
densité	<i>Noppenzahl</i>	ISO 1763	104,000 tufts/m ²
dimensions	<i>Breite</i>	CEN/TS 14159	ca. 4m / 5m
résistance thermique	<i>Wärmedurchlasswiderstand</i>	ISO 8302	0.13 m ² K/W
comportement au feu	<i>Brandverhalten</i>	ISO 13501-1	Bfl-s1
isolation acoustique	<i>Trittschallverbesserungsmaß</i>	ISO 140-8/717-2	25 dB

COLOURS

121 Ivory	329 Smoke	751 Marine
132 Mushroom	439 Pumice	753 Fox
136 Pebbles	724 Jade	
137 Clay	725 Piggy	

PRODIS RATING AND INFORMATION



EN 1307



PRODIS: A9EFE982

DOP: 1025-113822



CONTACT INFORMATION

THE NETHERLANDS
(HEAD OFFICE)
NIJVERHEIDSTRAAT 39
NL - 8281 JD GENEMUIDEN
+31 (0)38 385 22 11
info@edelpets.com
www.edelpets.com

geproduceerd door / manufactured by
fabriqué par / hergestellt durch



Alle technische specificaties zijn onderhevig aan productietoleranties. Voor alle voorwaarden en onderhoudsadvies verwijzen wij u graag naar onze website.

All specifications are subject to normal manufacturing tolerances. For all Terms & Conditions, care and maintenance, please visit our website.

Toutes les spécifications techniques sont sujet aux tolérances de fabrication. Merci de consulter notre website pour toutes informations et les conseils d'entretien.

Alle technische Daten unterliegen Produktionstoleranzen. Bedingungen und Pflegeempfehlungen finden Sie auf unserer Website.

v1