

2291 RYA


TECHNICAL SPECIFICATIONS ACCORDING TO EN 1307

constructie	<i>construction</i>	ISO 2424	1/4" 4 ply High low loop pile
poolmateriaal	<i>yarn content</i>	ISO 2424	90% NZ / 10% British Wool
rug	<i>backing</i>	ISO 2424	Starback
gebruiksklasse	<i>suitability</i>	EN 1307	22 general domestic use
poolgewicht	<i>pile weight</i>	ISO 2424	1225 gr/m ²
totaal gewicht	<i>total weight</i>	ISO 8543	2430 gr/m2
pooldikte	<i>pile height</i>	ISO 1766	5.0 mm / 8.5 mm
totaal dikte	<i>total thickness</i>	ISO 1765	5.5 mm/ 9.5 mm
noppental	<i>tuft density</i>	ISO 1763	46,000 tufts/m ²
breedte	<i>width</i>	CEN/TS 14159	ca. 4 m / ca. 5 m
warmtedoorlaatweerstand	<i>thermal resistance</i>	ISO 8302	0.14 m ² K/W
brandklasse	<i>flammability</i>	ISO 13501-1	Cfl-S1
contactgeluidsisolatie	<i>impact sound insulation</i>	ISO 140-8/717-2	25 dB
structure	<i>Konstruktion</i>	ISO 2424	Struktur Schlinge
composition	<i>Polmaterial</i>	ISO 2424	100% Schurwolle 4-ply
dossier	<i>Beschichtung</i>	ISO 2424	Starback
classement d'usage	<i>Zusatzeignung</i>	EN 1307	22 general domestic use
poids de velours	<i>Poleinsatzgewicht</i>	ISO 2424	1225 gr/m ²
poids total	<i>Gesamtgewicht</i>	ISO 8543	2430 gr/m2
hauteur du velours	<i>Polschichtdicke</i>	ISO 1766	5.0 mm / 8.5 mm
épaisseur totale	<i>Gesamtdicke</i>	ISO 1765	5.5 mm/ 9.5 mm
densité	<i>Noppenzahl</i>	ISO 1763	46,000 tufts/m ²
dimensions	<i>Breite</i>	CEN/TS 14159	ca. 4 m / ca. 5 m
résistance thermique	<i>Wärmedurchlasswiderstand</i>	ISO 8302	0.14 m ² K/W
comportement au feu	<i>Brandverhalten</i>	ISO 13501-1	Cfl-S1
isolation acoustique	<i>Trittschallverbesserungsmaß</i>	ISO 140-8/717-2	25 dB

COLOURS

112 Cream	139 Mouse
119 Pumice	179 Smoke
126 Amaranth	
132 Oats	

PRODIS RATING AND INFORMATION



EN 14041

EN 1307



PRODIS: 9DB5C152

DOP: 1025-126243

CONTACT INFORMATION

THE NETHERLANDS
(HEAD OFFICE)
NIJVERHEIDSTRAAT 39
NL - 8281 JD GENEMUIDEN
+31 (0)38 385 22 11
INFO@EDELCAVPETS.COM
WWW.EDELCAVPETS.COM

geproduceerd door / *manufactured by*
fabriqué par / *hergestellt durch*



Alle technische specificaties zijn onderhevig aan productietoleranties. Voor alle voorwaarden en onderhoudsadvies verwijzen wij u graag naar onze website.

All specifications are subject to normal manufacturing tolerances. For all Terms & Conditions, care and maintenance, please visit our website.

Toutes les spécifications techniques sont sujet aux tolérances de fabrication. Merci de consulter notre [site web](#) pour toutes informations et les conseils d'entretien.

Alle technische Daten unterliegen Produktionstoleranzen. Bedingungen und Pflegeempfehlungen finden Sie auf unserer Website.